



Natural Hydraulic Lime NHL 3.5

CE marked

PRODUCT SHEET

CHEMICAL CHARACTERISTICS	PHYSICAL CHARACTERISTICS	
SO ₃ < 1%	Compressive Strength (in MPa) 4 MPa < CS 28 days < 6 MPa	Setting Time (in hours minutes) Start > 2 H End < 10 H
	Fineness Undersize 90 ∞ > 92 % Undersize 200 ∞ > 98 %	Penetration (in mm) 25 mm < P < 30 mm
Free CaO < 15 %	Stability (in mm) S < 1 mm	Air Content (in % weight) AC < 10%
	Color Grey/Braun	Free Water (in % weight) FW < 1%

APPLICATIONS :

- Dry and pre-mix mortars
- Construction
- Building

CONDITIONING:

Paper bags of 50 kg, Big Bag and bulk